



銘安科技股份有限公司

MINIMA TECHNOLOGY CO., LTD.

Items	Name	GP9001A	GP9001F	Units
	MFR,190°C,2.16kgf	4.5	20	g/10min
	Density	1.26	1.26	g/cm ³
	Melting point	110	110	°C
	Tensile modulus	4284/6324	-	Kgf/cm ²
	Yield stress	357/357	357	Kgf/cm ²
	Stress at break	714/357	255	Kgf/cm ²
	Strain at break	550/220	100	%
	Elmendorf tear strength	3/5	-	N/mm
	Flexural modulus	-	520	Mpa
	Flexural strength	-	30	Mpa
	Molding shrinkage	-	1.0/1.0	%
	HDT(load 66psi)	-	90.0	°C
	Hardness,Shore			D
		Blowing	Injection	

* 以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制

*The Information herein is given in good faith, but no warranty, express or implied, is made. Consult the Company for further information